



CTI-300

齐聚物 · 单体 · 光引发剂 · 助剂

免责声明

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products。including intellectual property rights of third parties.

CTI-300 阳离子热引发剂

MW: 295

Density,g/cm³: 1.360

Curing condition : 70-150°C 3-15min

Form: 白色粉末

Viscosity at 25°C (50%inPC) : 260cps

CTI-300 是一款封闭型铈酸盐阳离子引发剂，解封温度低，溶解度高好，针对环氧化合物的固化反应活性高。或作为光固化引发剂的有效补充。在电子封装及 3D 打印，环氧复合成型等行业作为后固化反应的交联剂使主体树脂的最终固化更加充分，固化膜不黄变，无游离酸残留。